

遂宁宏明华瓷科技有限公司

承认书 APPROVAL SHEET

产 品 名 称 : 多层片式陶瓷电容器

PART NAME : MULTILAYER CERAMIC CAPACITORS

系 列 : 中高压系列(100V~3000V)

SERIES : Mid-High Volts Series(100V~3000V)

规 格 : 0402 ~ 1812 尺寸

SPECIFICATION: 0402 ~ 1812 Size

客 户: _____

供 应 商 (SUPPLIER) : 遂宁宏明华瓷科技有限公司

发布日期 (ISSUE DATE) : 20201116

批 准 (APPROVED BY) : _____

客户许可 (CUSTOMER APPROVAL) :

遂宁宏明华瓷科技有限公司

5、温度系数/特性 Temperature Coefficient /Characteristics


介质种类 Dielectric	参考温度点 Reference Temperature Point	标称温度系数 Temperature Coefficient	工作温度范围 Operation Temperature Range
C0G	20℃	0±30 ppm/℃	-55℃ ~ 125℃
C0H	20℃	0±60 ppm/℃	-55℃ ~ 125℃
X7R	20℃	±15%	-55℃ ~ 125℃
X7S	20℃	±22%	-55℃ ~ 125℃

备注：Ⅰ类电容器标称温度系数和允许偏差是采用温度在 20℃ 和 85℃ 之间的电容量变化来确定的，而Ⅱ类电容器标称温度系数是按照工作范围之间的电容量相对 20℃ 的电容量变化来确定的。

Note：Nominal temperature coefficient and allowed tolerance of class Ⅰ are decided by the changing of the capacitance between 20℃ and 85℃. Nominal temperature coefficient of class Ⅱ are decided by the temperature of 20℃.

6、产品外围尺寸及内部结构 EXTERNAL DIMENSIONS AND STRUCTURE


6-1 产品外围尺寸 Product peripheral dimension

外观 Outline	尺寸 Size Inch (mm)	长度 L (mm)	宽度 W (mm)	厚度 T (mm)/Symbol		焊接方式 SolderingMethod*	MB(mm)
	0402 (1005)	1.00±0.05	0.50±0.05	0.50±0.05	E	R	0.25±0.10
	0603 (1608)	1.60±0.20	0.80±0.20	0.80±0.20	H	R / W	0.40±0.15
	0805 (2012)	2.00±0.20	1.25±0.20	0.70±0.10	G	R / W	0.50±0.20
				0.80±0.20	H	R / W	
				1.25±0.20	L	R	
	1206 (3216)	3.20±0.20	1.60±0.20	0.80±0.20	H	R / W	0.60±0.20
				1.00±0.10	J	R	
				1.25±0.20	L		
				1.60±0.20	P		
	1210 (3225)	3.20±0.30	2.50±0.20	1.25±0.20	L	R	0.75±0.25
				1.60±0.20	P		
				2.00±0.20	U		
				2.50±0.20	V		
	1808 (4520)	4.5±0.40	2.0±0.25	1.25±0.20	L	R	0.75±0.25
				1.60±0.20	P		
				2.00±0.20	U		
	1812 (4532)	4.5±0.40	3.2±0.30	1.25±0.20	L	R	0.75±0.25
				1.60±0.20	P		
				2.00±0.20	U		
				2.50±0.30	V		

说明：R=Reflow Soldering 回流焊 W=Wave Soldering 波峰焊

遂宁宏明华瓷科技有限公司

6-2 结构 STRUCTURE



7、包装标准数量 PACKAGING STANDARD QUANTITY

Size 尺寸	Thickness (mm)/Symbol 厚度代码		Paper tape 纸带	Plastic Tape 胶带
			7"reel	7"reel
0402 (1005)	0.50±0.05	E	10,000	-----
0603 (1608)	0.80±0.20	H	4000	-----
0805 (2012)	0.70±0.10	G	4000	-----
	0.80±0.20	H	4000	-----
	1.25±0.20	L	-----	3000
1206 (3216)	0.70±0.10	G	4000	-----
	0.80±0.20	H	4000	-----
	1.00±0.10	J	-----	3000
	1.25±0.20	L	-----	3000
	1.60±0.20	P	-----	2000
1210 (3225)	1.25±0.20	L	-----	2000
	1.60±0.20	P	-----	2000
	2.00±0.20	U	-----	1000
	2.50±0.30	V	-----	1000
1808 (4520)	1.25±0.20	L		2000
	1.60±0.20	P		2000
	2.00±0.20	U		1000
1812(4532)	1.25±0.20	L	-----	1000
	1.60±0.20	P	-----	1000
	2.00±0.20	U	-----	1000
	2.50±0.30	V	-----	500

遂宁宏明华瓷科技有限公司

8、容量范围及其电压 Capacitance Range and rating Voltage

8-1 C0G/C0H 介质 Dielectric

DIELECTRIC				C0G/C0H																								
(尺寸) SIZE		0402		0603		0805				1206					1210				1808				1812					
RATED VOLTAGE (VDC)		100	250	100	200 250	100	200 250	500 630	1000	100	200 250	500 630	1000	1500 2000	200 250	500 630	1000	1500 2000	500 630	1000	1500 2000	3000	200 250	500 630	1000	1500 2000	3000	
Capacitance	0.5pF (0R5)	E	E	H	H	G	G	H	L																			
	1.0pF (1R0)	E	E	H	H	G	G	H	L																			
	1.2pF (1R2)	E	E	H	H	G	G	H	L																			
	1.5pF (1R5)	E	E	H	H	G	G	H	L	G	G	H	J	J														
	1.8pF (1R8)	E	E	H	H	G	G	H	L	G	G	H	J	J														
	2.2pF (2R2)	E	E	H	H	G	G	H	L	G	G	H	J	J														
	2.7pF (2R7)	E	E	H	H	G	G	H	L	G	G	H	J	J														
	3.3pF (3R3)	E	E	H	H	G	G	H	L	G	G	H	J	J														
	3.9pF (3R9)	E	E	H	H	G	G	H	L	G	G	H	J	J														
	4.7pF (4R7)	E	E	H	H	G	G	H	L	G	G	H	J	J														
	5.6pF (5R6)	E	E	H	H	G	G	H	L	G	G	H	J	J														
	6.8pF (6R8)	E	E	H	H	G	G	H	L	G	G	H	J	J														
	8.2pF (8R2)	E	E	H	H	G	G	H	L	G	G	H	J	J														
	10pF (100)	E	E	H	H	G	G	H	L	G	G	H	J	J	J	L	L	L	L	P	P	P	P	L	L	P	P	P
	12pF (120)	E	E	H	H	G	G	H	L	G	G	J	J	J	J	L	L	L	L	P	P	P	P	L	L	P	P	P
	15pF (150)	E	E	H	H	G	G	H	L	G	G	J	J	J	J	L	L	L	L	P	P	P	P	L	L	P	P	P
	18pF (180)	E	E	H	H	G	G	H	L	G	G	J	J	J	J	L	L	L	L	P	P	P	P	L	L	P	P	P
	22pF (220)	E	E	H	H	G	G	H	L	G	G	J	J	J	J	L	L	L	L	P	P	P	P	L	L	P	P	P
	27pF (270)	E	E	H	H	G	G	H	L	G	G	J	J	J	J	L	L	L	L	P	P	P	P	L	L	P	P	P
	33pF (330)	E	E	H	H	G	G	H	L	G	G	J	J	J	J	L	L	L	L	P	P	P	P	L	L	P	P	P
	39pF (390)	E	E	H	H	G	G	H	L	G	G	J	J	J	L	L	L	L	L	P	P	P	P	L	L	P	P	P
	47pF (470)	E	E	H	H	G	G	H	L	G	G	J	J	J	L	L	L	L	L	P	P	P	P	L	L	P	P	P
	56pF (560)	E		H	H	G	G	H		G	G	J	J	J	L	L	L	L	L	P	P	P	P	L	L	P	P	P
	68pF (680)	E		H	H	G	G	H		G	G	J	J	J	L	L	L	L	L	P	P	P	P	L	L	P	P	P
	82pF (820)	E		H	H	G	G	H		G	G	J	J	J	L	L	L	L	L	P	P	P	P	L	L	P	P	P
	100pF (101)	E		H	H	G	G	H		G	G	J	J	J	L	L	L	L	L	P	P	P	P	L	L	P	P	P
	120pF (121)			H	H	G	H	L		G	G	J	J	J		L	L	L	L	P	P	P		L	L	P	P	
	150pF (151)			H	H	G	H	L		G	G	J	L			L	L	L	L	P	P	P		L	L	P	P	
	180pF (181)			H	H	G	H	L		G	G	J	L			L	L	L	L	P	P	P		L	L	P	P	
	220pF (221)			H	H	G	H	L		G	G	J	L			L	L	L	L	P	P	P		L	L	P	P	
	270pF (271)			H	H	G	H	L		G	G	J	L			L	L	L		P	P			L	L	P	P	
	330pF (331)			H	H	G	H	L		H	H	J	L			L	L	L		P	P			L	L	P	P	
	390pF (391)			H	H	G	H			H	H	J				L	L	L		P	P			L	L	P		
	470pF (471)			H	H	G	H			H	H	J				L	L	L		P	P			L	L	P		
	560pF (561)			H	H	G	H			H	H	L				L	L	L		P	P			L	L	P		
	680pF (681)			H		G	H			H	H	L				L	L	L		P	P			L	L			
	820pF (821)			H		G	H			H	H	L				L	L			P	P			L	L			
	1,000pF (102)			H		G	H			H	H	L				L	L			P	P			L	L			
	1,200pF (122)					G				H						L	L			P				L	L			
	1,500pF (152)					G				H						L	P			P				L	L			
	1,800pF (182)					G				H						L	P			P				L	L			
	2,200pF (222)									H						L	P			P				L	L			
	2,700pF (272)															L				P				L				
	3,300pF (332)																			P				L				
	3,900pF (392)																			P				L				
	4,700pF (472)																			P				L				
	5,600pF (562)																							L				
	6,800pF (682)																							L				
	8,200pF (822)																							L				
	0.010μF (103)																							L				
0.012μF (123)																							L					
0.015μF (153)																							L					
0.018μF (183)																							L					
0.022μF (223)																							L					
0.027μF (273)																							L					
0.033μF (333)																							L					
0.039μF (393)																							L					
0.047μF (473)																							L					
0.056μF (563)																							L					
0.068μF (683)																							L					
0.082μF (823)																							L					
0.10μF (104)																							L					

遂宁宏明华瓷科技有限公司

8-2 X7R 介质 Dielectric

DIELECTRIC		X7R																									
SIZE		0603		0805			1206						1210					1808				1812					
RATED VOLTAGE (VDC)		100	200 250	100	200 250	500 630	100	200 250	500 630	1000	2000	2500	100	200 250	500 630	1000	1500 2000	500 630	1000	1500 2000	2500 3000	200 250	500 630	1000	1500 2000	3000	
Capacitance	100pF(101)	H	H	H	H	H	H	H	H	L	L	L	L	L	L	L	L										
	120pF(121)	H	H	H	H	H	H	H	H	L	L	L	L	L	L	L	L										
	150pF(151)	H	H	H	H	H	H	H	H	L	L	L	L	L	L	L	L	P	P	P	P						
	180pF(181)	H	H	H	H	H	H	H	H	L	L	L	L	L	L	L	L	P	P	P	P						
	220pF(221)	H	H	H	H	H	H	H	H	L	L	L	L	L	L	L	L	P	P	P	P						
	270pF(271)	H	H	H	H	H	H	H	H	L	L	L	L	L	L	L	L	P	P	P	P	P	P	P	P	P	
	330pF(331)	H	H	H	H	H	H	H	H	L	L	L	L	L	L	L	L	P	P	P	P	P	P	P	P	P	
	390pF(391)	H	H	H	H	H	H	H	H	L	L	L	L	L	L	L	L	P	P	P	P	P	P	P	P	P	
	470pF(471)	H	H	H	H	H	H	H	H	L	L	L	L	L	L	L	L	P	P	P	P	P	P	P	P	P	
	560pF(561)	H	H	H	H	H	H	H	H	L	L	L	L	L	L	L	L	P	P	P	P	P	P	P	P	P	
	680pF(681)	H	H	H	H	H	H	H	H	L	L	L	L	L	L	L	L	P	P	P	P	P	P	P	P	P	
	820pF(821)	H	H	H	H	H	H	H	H	L	L	L	L	L	L	L	L	P	P	P	P	P	P	P	P	P	
	1,000pF(102)	H	H	H	H	H	H	H	H	L	L	L	L	L	L	L	L	P	P	P	P	P	P	P	P	P	
	1,200pF(122)	H	H	H	H	H	H	H	H	L	L	P	L	L	L	L	L	P	P	P	P	P	P	P	P	P	
	1,500pF(152)	H	H	H	H	H	H	H	H	L	L	P	L	L	L	L	L	P	P	P	P	P	P	P	P	P	
	1,800pF(182)	H	H	H	H	H	H	H	H	L	L	P	L	L	L	L	L	P	P	P	P	P	P	P	P	P	
	2,200pF(222)	H	H	H	H	H	H	H	H	L	L	P	L	L	L	L	L	P	P	P	P	P	P	P	P	P	
	2,700pF(272)	H	H	H	H	H	H	H	H	L	L		L	L	L	L	L	P	P	P	P	P	P	P	P	P	
	3,300pF(332)	H	H	H	H	H	H	H	L	L	L		L	L	L	L	P	P	P	P	P	P	P	P	P	P	
	3,900pF(392)	H	H	H	H	H	H	H	L	L			L	L	L	L	P	P	P	P	P	P	P	P	P	P	
	4,700pF(472)	H	H	H	H	H	H	H	L	L			L	L	L	P	P	P	P	P	P	P	P	P	P	P	
	5,600pF(562)	H	H	H	H	H	H	H	L	L			L	L	L	P	P	P	P	P		P	P	P	P		
	6,800pF(682)	H	H	H	H	H	H	H	L	L			L	L	L	P	P	P	P			P	P	P	P		
	8,200pF(822)	H	H	H	H	L	H	H	L	L			L	L	L	P	P	P	P			P	P	P	P		
	0.010μF(103)	H	H	H	H	L	H	H	L	L			L	L	L	P	P	P	P			P	P	P	P		
	0.012μF(123)	H		H	H		H	H	L				L	L	L	P		P	P			P	P	P			
	0.015μF(153)	H		H	H		H	H	L				L	L	L	P		P	P			P	P	P			
	0.018μF(183)	H		H	H		H	H	L				L	L	L	P		P	P			P	P	P			
	0.022μF(223)	H		H	L		H	H	L				L	L	L	P		P				P	P	P			
	0.027μF(273)	H		L	L		H	H	L				L	L	L			P				P	P	P			
	0.033μF(333)	H		L	L		H	L	L				L	L	L			P				P	P	P			
	0.039μF(393)	H		L	L		H	L	L				L	L	L			P				P	P	P			
	0.047μF(473)	H		L	L		H	L	P				L	L	L			P				P	P	P			
	0.056μF(563)	H		L			H	L					L	L	L							P	P	S			
	0.068μF(683)	H		L			L	L					L	L	P							P	P	U			
	0.082μF(823)	H		L			L	L					L	L	P							P	P				
	0.10μF(104)	H		L			L	L					L	L	P							P	P	V			
	0.12μF(124)			L			L	L					L	L								P	P				
	0.15μF(154)			L			L	L					L	L								P	P				
	0.18μF(184)			L			L	P					L	P								P	P				
	0.22μF(224)			L			L	P					L	P								P	P				
	0.27μF(274)						L						P									P					
	0.33μF(334)						L						P									P					
	0.39μF(394)						P						P									P					
	0.47μF(474)						P						P									P					
	0.56μF(564)						P						P									P					
	0.68μF(684)						P						P									U					
	0.82μF(824)						P						P									U					
	1.0μF(105)						P						P									U					

遂宁宏明华瓷科技有限公司

9、可靠性测试 Reliability Test.

9-1 外观及电性能测试 Appearance and electrical performance test

编号 No.	项 目 Item		技 术 要 求 Technical requirements	测 试 方 法 Test Method and Remarks		
1	外观 Appearance		没有明显的缺陷或异常 No remarkable defects or abnormalities.	通过显微镜 (×10) Through microscope (×10)		
2	尺寸 size		在规定尺寸范围内 Within the specified size range	使用游标卡尺 Using a vernier caliper		
3	容量 Capacitance	I类 ClassI (C0G,C0H)	应符合指定的误差级别 Should be within the specified tolerance.	测试温度 Test temperature: 25±3℃ 测试条件 Test condition: C≤1000pF: 1MHz±10%, 1.0±0.2Vrms C > 1000pF: 1KHz±10%, 1.0±0.2Vrms		
		II类 Class II (X7R)	应符合指定的误差级别 Should be within the specified tolerance.	测试温度 Test temperature: 25±3℃ 测试条件 Test condition: C≤10μF: 1KHz±10%, 1.0±0.2Vrms C > 10μF: 120±24 Hz, 0.5±0.1Vrms 初始测量前 (仅限II类): 预处理*Before the initial measurement (only for class II):Note1		
4	损耗角正切 (DF, tanδ) Dissipation Factor	I类 ClassI (C0G,C0H)	损耗标准 DF Specification	标称容量 Capacitance	测试频率 Measuring Frequency	测试电压 Measuring Voltage
			≤0.56%	Cr < 5 pF	1MHz±10%	1.0±0.2Vrms
			1.5[(150/Cr)+7]×10 ⁻⁴	5pF≤Cr < 50 pF	1MHz±10%	
			≤0.15%	50pF≤Cr≤1000 pF	1MHz±10%	
			≤0.15%	> 1000 pF	1KHz±10%	
		II类 Class II (X7R)	≤2.5%	测试温度 Test temperature: 25±3℃ 测试条件 Test condition: C≤10μF: 1KHz±10%, 1.0±0.2Vrms C > 10μF: 120±24 Hz, 0.5±0.1Vrms		

遂宁宏明华瓷科技有限公司


第 7 页 共 19 页

编号 No.	项目 Item		技术要求 Technical requirements		测试方法 Test Method and Remarks	
5	绝缘电阻 (IR) Insulation Resistance	I类 Class I (C0G,C0H)	电容量范围 Capacitance range	绝缘电阻范围 Standard	测试电压 Measuring Voltage	额定电压 (最高 500V) Rated Voltage (Max 500V)
			C≤10 nF	Ri≥50000MΩ	测试时间 Duration	60±5 秒
			C > 10 nF	Ri•CR≥500S	测试电流 Charge/discharge current	≤50mA
		II类 Class II (X7R)	电容量范围 Capacitance range	绝缘电阻范围 Standard	测试温度 Test Temperature	25±3℃
			C≤25 nF	Ri≥10000MΩ	测试湿度 Test Humidity	≤75%
			C > 25 nF	Ri•CR > 100S		

9-2 可靠性测试：Reliability test

编号 No.	项目 Item	技术要求 Technical requirements	测试方法 Test Method and Remarks	
6	介质耐电强度 (DWV) Dielectric Withstanding Voltage	不应有介质被击穿或损伤 No breakdown or damage.	100V≤Vr < 500V:施加额定电压的 200%, 5 秒, 最大电流不超过 50mA/ Force 200%Rated voltage for 5 second.Max current should not exceed 50 mA.	
			500V≤Vr≤1000V:施加额定电压的 150%, 5 秒, 最大电流不超过 50mA/ Force 150%Rated voltage for 5 second.Max current should not exceed 50 mA.	
			1000V < Vr≤2000V:施加额定电压的 120%, 5 秒, 最大电流不超过 50mA/ Force 120%Rated voltage for 5 second.Max current should not exceed 50 mA.	
			2000V < Vr≤5000V:施加额定电压的 120%, 5 秒, 最大电流不超过 10mA/ Force 120%Rated voltage for 5 second.Max current should not exceed 10 mA.	
7	可焊性 Solderability	上锡率应大于 95%, 外观: 无可见损伤. At least 95% of the terminal electrode is covered by new solder. Visual Appearance: No visible damage.	将电容在 80~120℃的温度下预热 10~30 秒. Preheating conditions:80 to 120℃; 10~30s.	
			有铅焊料: (Sn/Pb: 63/37) 浸锡温度: 235±5℃ 浸锡时间: 2±0.5s Solder Temperature: 235±5℃ Duration: 2±0.5s	无铅焊料: 浸锡温度: 245±5℃ 浸锡时间: 2±0.5s Solder Temperature: 245±5℃ Duration: 2±0.5s

遂宁宏明华瓷科技有限公司

编号 No.	项目 Item	技术要求 Technical requirements	测试方法 Test Method and Remarks												
8	端头结合强度 Termination Adhesion	外观无可见损伤 No visible damage	施加的力 Applied Force: 0402&0603&0805: 5N; ≥1206:10N 时间 Duration: 10±1S												
9	耐焊接热 Resistance to Soldering Heat	1. 电性能要求: Electrical performance requirements <table><tr><td> 类别 classification 项目 Item </td><td>NPO (C0G、C0H)</td><td>X7R</td></tr><tr><td>ΔC/C</td><td>≤±0.5%</td><td>-5%~+10%</td></tr><tr><td>DF</td><td colspan="2">同初始标准 Same to initial value.</td></tr><tr><td>IR</td><td colspan="2">同初始标准 Same to initial value.</td></tr></table> 2.外观: 无可见损伤, 上锡率: ≥95% Appearance: No visible damage.At least 95% of the terminal electrode is covered by new solder.	类别 classification 项目 Item	NPO (C0G、C0H)	X7R	ΔC/C	≤±0.5%	-5%~+10%	DF	同初始标准 Same to initial value.		IR	同初始标准 Same to initial value.		初始测量前 (仅限II类): 预处理* 将电容在 100~200℃的温度下预热 2±0.5 分钟. 浸锡温度: 265±5℃ 浸锡时间: 10±1s 然后取出溶剂清洗干净,在 10 倍以上的显微镜底 下观察. 放置时间: 24±2 小时 放置条件: 室温 (1210 及以上规格采用回流焊方式试验) Before the initial measurement (only for class II):Note1 Preheating conditions: 100 to 200℃; 2±0.5min. Solder Temperature: 265±5℃ Duration: 10±1s Clean the capacitor with solvent and examine it with a 10X(min.) microscope. Recovery Time: 24±2h Recovery condition: Room temperature (1210 and Above: Reflow Soldering)
类别 classification 项目 Item	NPO (C0G、C0H)	X7R													
ΔC/C	≤±0.5%	-5%~+10%													
DF	同初始标准 Same to initial value.														
IR	同初始标准 Same to initial value.														
10	抗弯曲强度 Resistance to Flexure of Substrate (Bending Strength)	1、ΔC/C: ≤±10%; 2、外观: 无可见损伤. Appearance: No visible damage.	初始测量前 (仅限II类): 预处理* 试验基板 :PCB 厚度 : 1.6±0.2mm 弯曲 :1mm 施压速度 : 1mm/sec. 保持时间: 5±1s , 然后测量。 单位 Unit : mm  Before the initial measurement (only for class II):Note1 Test Board: PCB Thickness: 1.6±0.2mm Flexure :1mm. Pressurization Speed : 1mm/sec. Holding time: 5±1s ,Then measure.												

遂宁宏明华瓷科技有限公司

第 9 页 共 19 页

编号 No.	项目 Item	技术要求 Technical requirements	测 试 方 法 Test Method and Remarks																																					
11	潮湿 试验 (稳态) Moisture Resistance (Steady State)	ΔC/C	I类 (C0G,C0H) : ≤±2%或±1pF, 取两者之中较大者. II类 X7R: ≤±10% ClassI (C0G,C0H) : ≤±2% or ±1pF, whichever is larger. ClassII(X7R): ≤±10% ≤2 倍初始标准 Not more than twice of initial value. I类 (C0G,C0H): Ri≥2500MΩ或 Ri•CR≥25S 取两者之中较小者. ClassI (C0G,C0H) : Ri≥2500MΩ 或 Ri•CR≥25S whichever is smaller. II类 (X7R): Ri≥1000MΩ或 Ri•CR≥25S 取 两者之中较小者. ClassII (X7R) :Ri≥1000MΩ或 Ri•CR≥25S whichever is smaller. 外观 Appea rance 无损伤 No visible damage.																																					
		DF																																						
		IR																																						
外观 Appea rance																																								
12	温度循环 Temperature Cycle	<table><tr><td>类别</td><td>ΔC/C 标准</td></tr><tr><td>I类 (C0G,C0H)</td><td>≤±1%或±1pF , 取两者中最大者</td></tr><tr><td>II类 (X7R)</td><td>≤±10%</td></tr></table>		类别	ΔC/C 标准	I类 (C0G,C0H)	≤±1%或±1pF , 取两者中最大者	II类 (X7R)	≤±10%	1.预处理* (II类) 2.初始测量: 循环次数: 5 次,一个循环分以下 4 步: <table><tr><td>阶段</td><td>温度 (°C)</td><td>时间 (分钟)</td></tr><tr><td>第 1 步</td><td>下限温度: (-55)</td><td>30</td></tr><tr><td>第 2 步</td><td>常 温: (+20)</td><td>2 ~ 3</td></tr><tr><td>第 3 步</td><td>上限温度: (+125)</td><td>30</td></tr><tr><td>第 4 步</td><td>常 温: (+20)</td><td>2 ~ 3</td></tr></table> 3.放置时间: 24±2 小时, 放置条件: 室温, 然后测试。 1. Pretreatment (only for class2 capacitor): Note1. 2.Initial Measurement: Cycling Times: 5 times, 1 cycle, 4 steps: <table><tr><td>Step</td><td>Temperature (°C)</td><td>Time (min.)</td></tr><tr><td>1</td><td>Low- category temp. (-55)</td><td>30</td></tr><tr><td>2</td><td>Normal temp. (+20)</td><td>2 ~ 3</td></tr><tr><td>3</td><td>Up- category temp. (+125)</td><td>30</td></tr><tr><td>4</td><td>Normal temp. (+20)</td><td>2 ~ 3</td></tr></table> 3.Recovery Time: 24±2h, Recovery condition: Room temperature, then measure.	阶段	温度 (°C)	时间 (分钟)	第 1 步	下限温度: (-55)	30	第 2 步	常 温: (+20)	2 ~ 3	第 3 步	上限温度: (+125)	30	第 4 步	常 温: (+20)	2 ~ 3	Step	Temperature (°C)	Time (min.)	1	Low- category temp. (-55)	30	2	Normal temp. (+20)	2 ~ 3	3	Up- category temp. (+125)	30	4	Normal temp. (+20)	2 ~ 3
		类别	ΔC/C 标准																																					
		I类 (C0G,C0H)	≤±1%或±1pF , 取两者中最大者																																					
		II类 (X7R)	≤±10%																																					
		阶段	温度 (°C)	时间 (分钟)																																				
第 1 步	下限温度: (-55)	30																																						
第 2 步	常 温: (+20)	2 ~ 3																																						
第 3 步	上限温度: (+125)	30																																						
第 4 步	常 温: (+20)	2 ~ 3																																						
Step	Temperature (°C)	Time (min.)																																						
1	Low- category temp. (-55)	30																																						
2	Normal temp. (+20)	2 ~ 3																																						
3	Up- category temp. (+125)	30																																						
4	Normal temp. (+20)	2 ~ 3																																						
<table><tr><td>classification</td><td>ΔC/C standard</td></tr><tr><td>ClassI (C0G,C0H)</td><td>≤±1% or ±1pF, whichever is large</td></tr><tr><td>ClassII(X7R)</td><td>≤±10%</td></tr></table>		classification	ΔC/C standard	ClassI (C0G,C0H)	≤±1% or ±1pF, whichever is large	ClassII(X7R)	≤±10%																																	
classification	ΔC/C standard																																							
ClassI (C0G,C0H)	≤±1% or ±1pF, whichever is large																																							
ClassII(X7R)	≤±10%																																							

遂宁宏明华瓷科技有限公司

编号 No.	项目 Item	技术要求 Technical requirements	测 试 方 法 Test Method and Remarks		
13	耐久性 Durability	$\Delta C/C$ I类(C0G,C0H): $\leq \pm 2\%$ 或 $\pm 1pF$ 取两者之中较大者 II类(X7R): $\leq \pm 20\%$ ClassI(C0G,C0H): $\leq \pm 2\%$ or $\pm 1pF$, whichever is larger. ClassII(X7R): $\leq \pm 20\%$	电压 Applied Voltage:		
			项目	条件	
			< 500V 额定电压 < 500V Rated Voltage	2 倍工作电压 2 Multiple	
			500V $\leq$ 额定电压 $\leq$ 1000V 500V $\leq$ Rated Voltage $\leq$ 1000V	1.5 倍工作电压 1.5 Multiple	
		DF	≤ 2 倍初始标准 Not more than twice of initial value.	额定电压 > 1000V > 1000V Rated Voltage	1.2 倍工作电压 1.2 Multiple
		IR	I类(C0G,C0H): $R_i \geq 4000M\Omega$ 或 $R_i \bullet C_R \geq 40S$ 取两者之中较小者 ClassI(C0G,C0H): $R_i \geq 4000M\Omega$ 或 $R_i \bullet C_R \geq 40S$ whichever is smaller.	时间 Duration	1000 小时 h
			II类(X7R): $R_i \geq 2000M\Omega$ 或 $R_i \bullet C_R \geq 50S$,取两者之中较小者. ClassII(X7R): $R_i \geq 2000M\Omega$ 或 $R_i \bullet C_R \geq 50S$,whichever is smaller.	温度 Temperature	125℃
				充电电流 Charge/Discharge Current	不应超过 50mA 50mA max.
			外观 Appearance	室温下放置时间 Room temperature Recovery condition:	24 $\pm$ 2h
	无损伤 No visible damage.		试验前和试验后 (仅限II类): 预处理* Pre-test treatment and Post-test treatment (only for class II):Note1		

备注(Remark):

预处理* (仅对 2 类电容器):


将电容器放在上限类别温度或按详细规范中可能规定的更高温度下(150℃)经 1h 后,接着在试验的标准大气条件下恢复 24±1h.

Note1: Pretreatment (only for class2 capacitor)

Pretreatment (only for class2 capacitor) is a method to treat the capacitor before measurement. First, place the capacitor in the up-category temperature or other specified higher temperature environment (150℃) for 1hour. Then recovery the capacitor at standard pressure conditions for 24±1hours.


10、包装 PACKAGE

10-1 纸带卷盘结构 PAPER TAPING



遂宁宏明华瓷科技有限公司

10-1-1 0402 纸带编带尺寸大小。 Dimensions of paper taping for 0402 type.




单位 Unit: mm

代号 Code	A0	B0	W	F*	E	P1	P2*	P0	D0	T
0402	0.65± 0.10	1.15± 0.10	8.00± 0.10	3.50± 0.05	1.75± 0.10	2.00± 0.05	2.00± 0.05	4.00± 0.10	1.50 -0/+0.10	0.80 Below

注意：*表示此处对尺寸的要求非常精确。 Note: The place with “*” means where needs exactly dimensions.

10-1-2 0603, 0805, 1206, 常规尺寸产品的纸带尺寸。

Dimensions of paper taping for 0603, 0805, 1206 types.



纸带运行方向


单位 Unit: mm

代号Code 纸带规格 papersize	A	B	C	D*	E	F	G*	H	J	T
0603	1.10 ± 0.10	1.90 ± 0.10	8.00 ± 0.10	3.50 ± 0.05	1.75 ± 0.10	4.00 ± 0.10	2.00 ± 0.10	4.00 ± 0.10	1.50 -0/+0.10	1.10 Max
0805	1.45 ± 0.15	2.30 ± 0.15	8.0 ± 0.15	3.50 ± 0.05	1.75 ± 0.10	4.00 ± 0.10	2.00 ± 0.10	4.00 ± 0.10	1.50 -0/+0.10	1.10 Max
1206	1.80 ± 0.20	3.40 ± 0.20	8.00 ± 0.20	3.50 ± 0.05	1.75 ± 0.10	4.00 ± 0.10	2.00 ± 0.10	4.00 ± 0.10	1.50 -0/+0.10	1.10 Max


遂宁宏明华瓷科技有限公司

注意：*表示此处对尺寸的要求非常精确。 Note: The place with“*”means where needs exactly dimensions.

10-2 塑胶卷盘结构 EMBOSSED TAPING



10-2-1 塑胶带尺寸结构 (适合‘0805~1812’型产品)。
Dimensions of embossed taping for 0805~1812 type.




Unit: mm

代号 Code 规格 Tape size	A	B	C	D*	E	F	G*	H	J	T
0805	1.55 ± 0.20	2.35 ± 0.20	8.00 ± 0.20	3.50 ± 0.05	1.75 ± 0.10	4.00 ± 0.10	2.00 ± 0.10	4.00 ± 0.10	1.50 -0/+0.10	1.50 Max
1206	1.95 ± 0.20	3.60 ± 0.20	8.00 ± 0.20	3.50 ± 0.05	1.75 ± 0.10	4.00 ± 0.10	2.00 ± 0.10	4.00 ± 0.1	1.50 -0/+0.10	1.85 Max
1210	2.70 ± 0.10	3.42 ± 0.10	8.00 ± 0.10	3.50 ± 0.05	1.75 ± 0.10	4.00 ± 0.10	2.00 ± 0.05	4.00 ± 0.10	1.55 -0/+0.10	3.2 Max
1808	2.20 ± 0.10	4.95 ± 0.10	12.00 ± 0.10	5.50 ± 0.05	1.75 ± 0.10	4.00 ± 0.10	2.00 ± 0.05	4.00 ± 0.10	1.50 -0/+0.10	3.0 Max
1812	3.66 ± 0.10	4.95 ± 0.10	12.00 ± 0.10	5.50 ± 0.05	1.75 ± 0.10	8.00 ± 0.10	2.00 ± 0.05	4.00 ± 0.10	1.55 -0/+0.10	4.0 Max

遂宁宏明华瓷科技有限公司


备注：*表示此处对尺寸的要求非常精确。 Note：The place with “*” means where needs exactly dimensions.

10-3 传送带的前后结构 Structure of leader part and end part of the carrier paper



10-3-1 卷盘尺寸 Reel Dimensions

尺寸代码 (CODE)	Unit: mm						
卷盘型号	A	B	C	D	E	F	G
8mm/7REEL	$\phi 178 \pm 2.0$	3.0	$\phi 13 \pm 0.5$	$\phi 21 \pm 0.8$	$\phi 50$ 或更大 $\phi 50$ or more	100 ± 1.5	14.4max
13'REEL	$\phi 330 \pm 2.0$	3.0	$\phi 13 \pm 0.5$	$\phi 21 \pm 0.8$	$\phi 50$ 或更大 $\phi 50$ or more	100 ± 1.5	14.4max
12mm/7REEL	$\phi 178 \pm 2.0$	3.0	$\phi 13 \pm 0.5$	$\phi 21 \pm 0.8$	$\phi 50$ 或更大 $\phi 50$ or more	13.4 ± 1.5	18.4max




10-4 卷带的说明 Taping specification

面胶剥离强度 Top tape peeling strength

(a) 纸带 Paper Taping

遂宁宏明华瓷科技有限公司

第 14 页 共 19 页




标准：0.1N<剥离强度<0.7N。 Standard: 0.1N < peeling strength < 0.7N

在剥离时，纸带不能有纸碎，也不能粘在底、面胶上。

No paper dirty remains on the scotch when peeling, and sticks to top and bottom tape.

(b) 塑料胶盘 Embossed Taping



标准：0.1N<剥离强度<0.7N。 Standard: 0.1N < peeling strength < 0.7N

11、储存方法 Storage Methods

确保芯片可焊性良好的贮存期限为 6 个月(在包装好已交付的情况下)。

The guaranteed period for solderability is 6 months (Under deliver package condition).

储存条件/Storage conditions:

储存温度/Temperature $5^\circ\text{C} \sim 40^\circ\text{C}$

储存相对湿度/Relative Humidity 20%~70%

12、使用前的注意事项 Precautions For Use

多层片式瓷介电容器(MLCC)在短路或开路的电路中都有可能失效,在超出本承认书或相关说明书中所述使用频率的恶劣工作环境,或外界机械力超压作用下,电容芯片都有可能着火、燃烧甚至爆炸,所以在使用的時候,首先应考虑按本承认书的有关说明来进行,如有不明之处,请联系我们技术部门。

遂宁宏明华瓷科技有限公司

第 15 页 共 19 页

The Multi-layer Ceramic Capacitors (MLCC) may fail in a short circuit mode in an open circuit mode when subjected to severe conditions of electrical environment and / or mechanical stress beyond the specified “rating” and specified “conditions” in the specification, which will result in burn out, flaming or glowing in the worst case. Following “precautions for “safety” and Application Notes shall be taken in your major consideration. If you have a question about the precautions for handling, please contact our engineering section or factory.

12-1. 焊接的条件与相关图表 Soldering Profile

为避免因温度的突然变化而引起的芯片开裂或局部爆炸的现象发生,请按有关温度曲线图表来进行.
(请参考附页中的图表)

To avoid the crack problem by sudden temperature change, follow the temperature profile in the adjacent graph(refer to the graph in the enclosure page).

12-2 手工焊接 Manual Soldering


手工焊接很容易因为芯片局部受热不均而引起瓷体微裂或局部爆炸的现象,在焊接时,如果操作者不小心,会使烙铁头直接同电容芯片的瓷体部分接触,这样很容易使电容芯片因热冲击而受损或出现其他意外.因此,使用电烙铁手工焊接时应仔细操作,并对电烙铁的尖端的选择和尖端温度控制应多加小心.

Manual soldering can pose a great risk of creating thermal cracks in capacitors. The hot soldering iron tip comes into direct contact with the end terminations, and operator’s careless may cause the tip of the soldering iron to come into direct contact with the ceramic body of the capacitor. Therefore the soldering iron must be handled carefully, and pay much attention to the selection of the soldering iron tip and temperature contact of the tip.

12-3 适量的焊料 Optimum Solder Amount for Reflow Soldering

焊料过多

Too much solder




这样会因端头压力过大而
可能引起芯片受损

Cracks tend to occur due to large stress.

焊料太少

Not enough solder




固定力量不足,可能会引起
电容芯片与线路接触不良
Weak holding force may cause bad connection
between the capacitor and PCB.

遂宁宏明华瓷科技有限公司

12-4 推荐焊料用量 Recommended Soldering amounts


回流焊接的最佳焊料用量

The optimal solder fillet amounts for re-flow soldering




波峰焊接的最佳焊料用量

The optimal solder fillet amounts for wave soldering




使用烙铁返修时的最佳焊料量

The optimal solder fillet amounts for reworking




12-5 推荐焊接温度曲线图 The temperature profile for soldering

12-5-1 回流焊接 (Re-flow soldering)



有铅回流焊曲线 SnPb Reflow soldering profile

遂宁宏明华瓷科技有限公司



无铅回流焊曲线 Lead-free Reflow soldering profile


在预热时，需尽可能缩小焊接温度与芯片表面温度之间的温差，如表 1 所示。
While in preheating, It is required to keep the temperature differential(ΔT) between soldering temperature and the components surface as small as possible, shown in the table 1.

表 1 (table 1)

类型 type	温差 Temperature differential ΔT
HHV0603/ HHV0805/ HHV1206	$\Delta T \leq 150^{\circ}\text{C}$
HHV1210/HHV1808/HHV1812	$\Delta T \leq 130^{\circ}\text{C}$

遂宁宏明华瓷科技有限公司

12-5-2 波峰焊接 (Wave soldering)



波峰焊曲线 Wave soldering profile

在预热时，需尽可能缩小焊接温度与芯片表面温度之间的温差，如表 2 所示。
While in preheating, It is required to keep the temperature differential(ΔT) between soldering temperature and the components surface as small as possible, shown in the table 2.

表 2 (table 2)

类型 type	温差 Temperature differential ΔT
HHV0603/ HHV0805/ HHV1206	$\Delta T \leq 150^{\circ}\text{C}$

12-5-3 手工焊接 (Hand soldering)


条件 Conditions:

预热 Preheating	烙铁头温度 Temperature of soldering iron head	烙铁功率 Power Of soldering iron	烙铁头直径 Diameter of soldering iron head	焊接时间 Soldering time	锡膏量 Solder paste amount	限制条件 Restricted conditions
$\Delta \leq 130^{\circ}\text{C}$	最高 350°C Highest temperature:350 °C	最大 20W 20W at the highest	建议 1mm 1mm recommended	最长 3s 3s at the longest	$\leq 1/2$ 芯片厚度 $\leq 1/2$ chip thickness	请勿使用烙铁头直接 接触陶瓷元件 Please avoid the direct contact between soldering iron head and ceramic components


遂宁宏明华瓷科技有限公司

13、典型的特性数据曲线图 Typical characteristic data graph


1、|Z|-频率特性曲线 |Z| - Frequency Characteristics



2、温度特性 Temperature Characteristics



3、直流偏压特性 DC Bias Characteristics



注：以上产品特性仅供参考。

Note: The above product characteristics are for reference only.